‡ Fermilab

Fermi National Accelerator Laboratory

Technical Division-Machine Shop

Procedure Qualification Record No. Fermi PQR SS-8-001

Date: 12/7/2009

Revision: __ Date: _____

Remarks:


Welding Process/Weld Type: GTAW/Manual

In accordance with:

Fermi WPS SS-8-001

Joints (OW-402)

Weld Type:	Square Butt Groove
Backing:	No Backer/Gas Only
Root Opening:	No Opening
Root Face:	.035"



Base Metals (QW-403)		Post Weld Heat Treatment (QW-407)		
Material Spec., Type or Grade:		Type:	No PWHT performed	
SA 240 plate type 304	To	SA 240 plate type 304	Temperat	ure:
P Number: 8, Group 1 To	P Nu	mber: 8, Group1	Time:	
Thickness of Coupon (in.)	.035	,		
Diameter of Test Coupon (in.)	Plate			
	•			

Filler Metals (QW-404)		Gas (QW-408) Percent Composition		nposition	
SFA Specification	5.9		Gas	Mixture%	Flow Rate
AWS Classification:	308/308L	Shielding	Argon	99.99%	15 CFH
Filler Metal F-No.:	F6	Trailing:	None		
Weld Metal Analysis A-No.:	8	Backing:	Argon	99.99%	15 CFH
Size of Filler Metal (in.):	.035"	Other: Maintain Argon purge on backside of plate fo			ckside of plate for
Weld Deposit "t"(in.):	.035"	entire weld. Use alignment fixture to position plates			o position plates
Filler Metal Product Form:	Bare Wire/Solid	for welding	and purg	ing. Non-Pulsir	ig Current

Positions (QW-405)		Electrical Characteristics (QW-409)
Position of Joint:	Flat-1G	Current/Polarity:DCEN
Weld Progression:		Amps: 40-48 Volts: 8-12
Other:		Tungsten Type & Size:
		Other: Non-Pulsing Current

Preheat (QW-406)		Technique (QW-410)	
Preheat Temperature:	50 ° F Minimum	Travel (ipm): As Required	Oscillation: None
Interpass Temperature:	350° F Maximum	String/Weave Bead :	Stringer
Minimum Weld Temp.	32 ° F	Multiple/Single Pass:	Single
		Multiple/Single Electrode :	Single Electrode
		Nozzle/Gas Cup Size:	#6

*	Ferm	nilab
---	------	-------

Welder's Name: William Gatfield

Fermi National Accelerator Laboratory

Technical Division-Machine Shop

W-12

Weld Stamp :

	I constant Division Machine Site					
Procedure Qualification Record	No. Fermi PQR SS-8-001	Date: 12/7/2009				
Welding Process/Weld Type: GTAW/Manu	al WPS No.: Fermi WP	S SS-8-001				

Tensile Test (OW-150)

		TOTISHE TOST	(211 200)		
Specimen		Area	Ultimate Total	Ultimate	Failure Type
No.	Dimensions	(Squared in.)	Load (lbs.)	Stress (PSI)	& Location
001	0.0348 x 0.7500	0.0261	2802.0	107400	HAZ/ Ductile
002	0.0378 x 0.7540	0.0285	2684.0	94200	Weld/Ductile

Guided Bend Test (QW-160)

Figure Number & Type	Result	Figure Number Type	Result
QW-462.3 (a) Face Bend	Pass-No Visible Cracks	QW-462.3 (a) Root Bend	Pass-No Visible Cracks
QW-462.3 (a) Face Bend	Pass-No Visible Cracks	QW-462.3 (a) Root Bend	Pass-No Visible Cracks

ю: 04609N

Visual Examination: <u>Acceptable</u> X-ray per ASM	E Section IX, QW-19	1.2.	
Radiography Conducted By: N/A	T		
Tests Conducted by: Exova Inc.	T914242	Date: 12/07/2	2009
2000 Conducted by: 20070 me.			

We certify that the statements in this record are correct and that the test welds were prepared, welded, and tested in accordance with the requirements of Section IX of the ASME Code.

PQR prepared by: Fermi National Accelerator Laboratory

Authorized Representative	Jugar 4	Hiller	Date:	_12/07/2010	
•					

Use of Fermilab Welding Procedures and Welder Qualifications for non-Fermilab work shall be at the sole risk and responsibility of the Subcontractor, and the Subcontractor shall indemnify and save Fermilab and the government harmless from any and all claims, demands, actions or causes of action, and for any expense or loss by reason of Subcontractor's and their employees possession and use of Fermilab procedures and qualifications.